



A top-rate adhesive polyethylene stretch film is obtained by a simultaneous extrusion process of four different prelaminated layers. Designed for palletizing loads of any kind, it can be used on fully automatic power-stretch machines up to 220% for the FPS, and up to 280% for the 18K. It comes also with an anti-UV treatment to resolve problems which may arise with loads stored out door.



■ TECHNICAL INFORMATIONS

| PROPERTIES | | STANDARD | MEASURE UNIT | VALUE |
|---------------------|-------|----------------------|--------------------|-------|
| BREAKING STRENGTH | LONG | ASTM D 882 | KG mm ² | 5 |
| | TRASV | | | 3 |
| ELONGATION STRENGTH | LONG | ASTM D 882 | % | 570 |
| | TRASV | | | 800 |
| TEAR STRENGTH | LONG | ASTM D 1922 | Gr. | 200 |
| | TRASV | | | 260 |
| PUNCTURE STRENGTH | | DERIBLOK'S OWN NORMS | Gr. | 2000 |
| DART TEST | | ASTM D 1709 | Gr. | 170 |
| GLOSS | | ASTM D 2457 | % | 91 |
| SLIP | | ASTM D 1894 | - | > 1 |

